

SEMPERIT ()

DIN EN 857 1 SC









Compact Hydraulic Hose construction acc. to DIN EN 857 1 SC



HOSE:	
Tube	Synthetic rubber, resistant against hydraulic fluids (HL, HLP, HLPD, HVLP, HFA, HFAS, HFB, HFC)
Reinforcement	One braid of high tensile steel wire
Cover	Abrasion and ozone resistant synthetic rubber Note: various covers available
Temperature range	-40°C to 100°C / -40°F to +212°F (max 120°C/248°F intermittent)
Standard Branding	embossed

SEMPERIT S	DIN EN 857 1SC	DN 10	WP 180 BAR	2610 PSI	Q . W . z	
	DII 1 1 001 100	D14 10	THE TOO DATE	2010101		

Nominal Ø		Inside Ø	Braid Ø	Outside Ø	Working pressure		Test pressure	Burst pressure	Bend radius	Weight
mm	inch	mm	mm	mm	bar	psi	bar	bar	mm	kg/m
6	1/4	6,6	9,9	11,9	225	3265	450	900	75	0,16
8	5/16	8,3	11,7	13,7	215	3120	430	860	85	0,21
10	3/8	9,9	13,1	15,7	180	2610	360	720	90	0,26
12	1/2	13,0	16,6	19,5	160	2320	320	640	130	0,34
16	5/8	16,4	20,3	22,3	130	1885	260	520	150	0,39
19	3/4	19,5	24,0	26,0	105	1525	210	420	180	0,50
25	1	26	31,0	33,1	88	1275	176	352	230	0,74

Publication date: April 2013 - Subject to changes without notice

Important Notice:

Important Notice:
This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The choice of the correct type of hose is very important for the proper and safe use in service. Check your or your customer's specific application accordingly and instruct on limits and dangers of product use accurately. Application, use and processing of our products or your products manufactured on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Check for operating safety regularly. In the event of damage, in particular to the hose cover, hoses must be replaced for safety reasons.



Wrong product selection, installation or improper treatment (such as crushing, tearing, stretching, loading with impermissible media and bending radius lower than specified) of the hoses can result in damage or failure of the hose, (often also serious) material damage and personal injury.



A MEMBER OF THE SEMPERIT-GROUP